



Amar International

100% CARDED COTTON RINGSPUN YARNS

CARDED WEAVING YARNS

Sr. No.	Count of Yarn	Actual Count	Count CV%	CSP	Strength CV%	RKM gm/ Tex UTR	Elongation%	U%	Total Imperfection/km	Total Classmate/km	Hairiness	sh	T.P.I.	T.M.
1	NE 10/1 CARDED WEAVING	10.3	1.3	2800	4.5	19.5	5.0	8.9	50	100	8.5	2.0	13.0	4.1
2	NE 12/1 CARDED WEAVING	12.3	1.4	2800	4.5	19.5	5.0	9.0	100	100	8.3	2.0	14.2	4.1
3	NE 16/1 CARDED WEAVING	16.3	1.5	2700	4.5	19.0	5.0	9.3	180	180	8.0	2.0	16.4	4.2
4	NE 20/1 CARDED WEAVING	20.3	1.5	2700	4.5	19.0	4.8	10.3	250	200	7.5	2.0	19.2	4.3
5	NE 21/1 CARDED WEAVING	21.3	1.5	2700	4.5	19.0	5.0	10.5	250	200	7.5	2.0	19.7	4.3
6	NE 24/1 CARDED WEAVING	24.3	1.5	2700	4.5	19.0	4.5	11.0	350	250	7.0	2.0	21.1	4.3
7	NE 28/1 CARDED WEAVING	28.3	1.5	2650	4.5	19.0	4.5	11.0	700	250	7.0	2.0	22.8	4.3
8	NE 30/1 CARDED WEAVING	30.3	1.5	2650	4.5	19.0	4.5	11.0	700	300	7.0	2.0	23.6	4.3
9	NE 32/1 CARDED WEAVING	32.3	1.5	2650	4.5	19.0	4.5	11.5	750	350	6.8	2.0	24.3	4.3
10	NE 36/1 CARDED WEAVING	36.3	1.5	2600	4.5	18.5	4.3	12.0	900	400	6.5	2.0	25.8	4.3
11	NE 40/1 CARDED WEAVING	40.3	1.5	2550	4.5	18.0	4.2	12.0	1100	450	6.0	2.0	27.2	4.3