



Amar International

100% COMBED COTTON RINGSPUN YARNS

COMBED KNITTING YARNS

| Sr. No. | Count of Yarn | Actual Count | Count CV% | CSP | Strength CV% | RKM gm/ Tex UTR | Elongation% | U% | Total Imperfection/km | Total Classmate/km | Hairiness | sh | T.P.I. | T.M. |
|---------|--------------------------|--------------|-----------|------|--------------|-----------------|-------------|------|-----------------------|--------------------|-----------|-----|--------|------|
| 1 | NE 16/1 COMBED KNITTING | 16 | 1.5 | 2450 | 4.5 | 18.0 | 4.7 | 8.0 | 25 | 80 | 6.0 | 2.0 | 14.6 | 3.7 |
| 2 | NE 20/1 COMBED KNITTING | 20 | 1.5 | 2450 | 4.5 | 18.0 | 4.7 | 8.0 | 30 | 80 | 6.0 | 2.0 | 16.3 | 3.7 |
| 3 | NE 21/1 COMBED KNITTING | 21 | 1.5 | 2450 | 4.5 | 18.0 | 4.7 | 8.5 | 30 | 80 | 6.0 | 2.0 | 16.7 | 3.7 |
| 4 | NE 24/1 COMBED KNITTING | 24 | 1.5 | 2450 | 4.5 | 18.0 | 4.7 | 9.0 | 40 | 80 | 6.0 | 2.0 | 17.9 | 3.7 |
| 5 | NE 26/1 COMBED KNITTING | 26 | 1.5 | 2450 | 4.5 | 18.0 | 4.7 | 9.0 | 45 | 80 | 6.0 | 2.0 | 18.6 | 3.7 |
| 6 | NE 28/1 COMBED KNITTING | 28 | 1.5 | 2450 | 4.5 | 18.0 | 4.7 | 9.2 | 50 | 80 | 6.0 | 2.0 | 19.3 | 3.7 |
| 7 | NE 30/1 COMBED KNITTING | 30 | 1.5 | 2450 | 4.5 | 17.0 | 4.7 | 9.4 | 55 | 80 | 5.5 | 2.0 | 20.0 | 3.7 |
| 8 | NE 32/1 COMBED KNITTING | 32 | 1.5 | 2450 | 4.5 | 17.0 | 4.7 | 9.4 | 60 | 80 | 5.5 | 2.0 | 20.6 | 3.7 |
| 9 | NE 34/1 COMBED KNITTING | 34 | 1.5 | 2450 | 4.5 | 17.0 | 4.7 | 9.6 | 65 | 80 | 5.5 | 2.0 | 21.3 | 3.7 |
| 10 | NE 36/1 COMBED KNITTING | 36 | 1.5 | 2450 | 4.5 | 17.0 | 4.7 | 9.6 | 75 | 90 | 5.5 | 2.0 | 21.9 | 3.7 |
| 11 | NE 40/1 COMBED KNITTING | 40 | 1.5 | 2450 | 4.5 | 17.0 | 4.7 | 9.8 | 80 | 100 | 4.8 | 2.0 | 23.1 | 3.7 |
| 12 | NE 50/1 COMBED KNITTING | 50 | 1.5 | 2400 | 5.0 | 17.0 | 4.7 | 11.8 | 120 | 120 | 4.8 | 2.0 | 25.8 | 3.7 |
| 13 | NE 60/1 COMBED KNITTING | 60 | 2.0 | 2400 | 5.0 | 17.0 | 4.7 | 12.0 | 150 | 130 | 3.0 | 2.0 | 28.3 | 3.7 |
| 14 | NE 80/1 COMBED KNITTING | 80 | 2.0 | 2350 | 5.0 | 16.0 | 4.7 | 12.0 | 250 | 300 | 3.0 | 2.0 | 32.6 | 3.7 |
| 15 | NE 100/1 COMBED KNITTING | 100 | 2.0 | 2350 | 5.0 | 16.0 | 4.7 | 12.5 | 550 | 500 | 2.7 | 2.0 | 36.5 | 3.7 |
| 16 | NE 120/1 COMBED KNITTING | 120 | 2.0 | 2350 | 5.0 | 15.0 | 4.7 | 12.5 | 700 | 650 | 2.7 | 2.0 | 40.0 | 3.7 |