



Amar International

100% COMBED COTTON RINGSPUN YARNS

COMBED WEAVING YARNS

Sr. No.	Count of Yarn	Actual Count	Count CV%	CSP	Strength CV%	RKM gm/ Tex UTR	Elongation%	U%	Total Imperfection/km	Total Classmate/km	Hairiness	sh	T.P.I.	T.M.
1	NE 16/1 COMBED WEAVING	16.3	1.3	3000	4.3	20.5	5.5	8.0	25	15	8.5	2.3	16.1	4.0
2	NE 20/1 COMBED WEAVING	20.3	1.3	3000	4.4	20.5	5.4	8.5	25	20	8.5	2.3	18.0	4.0
3	NE 21/1 COMBED WEAVING	21.3	1.5	2900	4.5	20.0	5.3	8.7	30	25	8.3	2.3	18.5	4.0
4	NE 24/1 COMBED WEAVING	24.3	1.5	2900	4.5	20.0	5.3	8.7	35	35	8.3	2.3	19.7	4.0
5	NE 26/1 COMBED WEAVING	26.3	1.5	2900	4.5	20.0	5.2	8.9	45	35	8.2	2.0	20.5	4.0
6	NE 28/1 COMBED WEAVING	28.3	1.5	2900	4.5	20.0	5.1	9.0	45	40	8.2	2.0	21.3	4.0
7	NE 30/1 COMBED WEAVING	30.3	1.5	2900	4.5	20.0	5.0	9.5	50	60	8.0	2.0	22.0	4.0
8	NE 32/1 COMBED WEAVING	32.3	1.5	2900	4.5	20.0	5.0	9.5	65	65	8.0	2.0	22.7	4.0
9	NE 34/1 COMBED WEAVING	34.3	1.5	2850	4.5	20.0	5.0	10.0	70	65	7.8	2.0	23.4	4.0
10	NE 36/1 COMBED WEAVING	36.3	1.5	2850	4.5	20.0	4.8	10.0	90	65	7.5	2.0	24.1	4.0
11	NE 40/1 COMBED WEAVING	40.3	1.5	2800	5.0	20.0	4.0	10.5	100	120	6.8	2.0	25.4	4.0
12	NE 50/1 COMBED WEAVING	50.3	1.5	2800	5.0	20.0	4.0	11.0	160	200	6.0	1.3	28.4	4.0
13	NE 60/1 COMBED WEAVING	60.3	1.5	2800	5.0	20.0	4.0	11.5	250	300	5.3	1.0	31.1	4.0
14	NE 80/1 COMBED WEAVING	80.3	2.0	2750	5.5	20.0	4.0	12.0	300	500	5.0	1.0	35.8	4.0
15	NE 100/1 COMBED WEAVING	100.3	2.0	2750	5.5	19.5	4.0	12.5	400	650	4.5	0.9	40.1	4.0
16	NE 120/1 COMBED WEAVING	120.3	2.0	2650	5.5	19.5	4.0	12.5	500	800	4.5	0.9	43.9	4.0