



*Amar International*

## 100% COMBED COMPACT COTTON RINGSPUN YARNS

### COMBED COMPACT KNITTING YARNS

Sr. No.	Count of Yarn	Actual Count	Count CV%	CSP	Strength CV%	RKM gm/ Tex UTR	Elongation%	U%	Total Imperfection/km	Total Classmate/km	Hairiness	T.P.I.	T.M.
1	NE 20/1 COMBED COMPACT KNITTING	20	1.5	3000	4.5	19.0	5.0	7.0	15	40	6.5	15.7	3.5
2	NE 21/1 COMBED COMPACT KNITTING	21	1.5	3000	4.5	19.0	5.0	7.0	15	40	6.2	16.0	3.5
3	NE 24/1 COMBED COMPACT KNITTING	24	1.5	2850	4.5	19.0	5.0	7.5	30	40	6.0	17.1	3.5
4	NE 26/1 COMBED COMPACT KNITTING	26	1.5	2850	4.5	19.0	4.7	7.5	35	40	6.0	17.8	3.5
5	NE 30/1 COMBED COMPACT KNITTING	30	1.5	2850	4.5	19.0	4.7	8.0	45	40	5.5	19.2	3.5
6	NE 32/1 COMBED COMPACT KNITTING	32	1.5	2850	4.5	19.0	4.7	8.0	50	40	5.5	19.8	3.5
7	NE 34/1 COMBED COMPACT KNITTING	34	1.5	2850	4.5	19.0	4.7	8.5	55	40	5.0	20.4	3.5
8	NE 36/1 COMBED COMPACT KNITTING	36	1.5	2850	4.5	19.0	4.5	8.5	60	50	5.0	21.0	3.5
9	NE 40/1 COMBED COMPACT KNITTING	40	1.5	2850	5.0	19.0	4.5	9.0	65	70	4.5	22.1	3.5
10	NE 50/1 COMBED COMPACT KNITTING	50	1.5	2750	5.0	18.0	4.5	9.2	100	100	4.0	24.7	3.5
11	NE 60/1 COMBED COMPACT KNITTING	60	2.0	2750	5.0	18.0	4.5	9.5	115	150	3.0	27.1	3.5
12	NE 80/1 COMBED COMPACT KNITTING	80	2.0	2750	5.0	18.0	4.2	10.0	225	200	3.0	31.3	3.5
13	NE 100/1 COMBED COMPACT KNITTING	100	2.0	2750	5.0	17.6	4.2	10.5	250	300	2.8	35.0	3.5
14	NE 120/1 COMBED COMPACT KNITTING	120	2.0	2750	5.0	17.6	4.0	11.0	300	350	2.8	38.3	3.5