



Amar International

100% COMBED COMPACT COTTON RINGSPUN YARNS

COMBED COMPACT WEAVING YARNS

Sr. No.	Count of Yarn	Actual Count	Count CV%	CSP	Strength CV%	RKM gm/ Tex UTR	Elongation%	U%	Total Imperfection/km	Total Classmate/km	Hairiness	sh	T.P.I.	T.M.
1	NE 20/1 COMBED COMPACT WEAVING	20.3	1.5	3400	4.5	23.0	5.0	7.0	20	35	5.0	1.0	17.6	3.9
2	NE 21/1 COMBED COMPACT WEAVING	21.3	1.5	3400	4.5	23.0	5.0	7.0	20	35	5.0	1.0	18.0	3.9
3	NE 24/1 COMBED COMPACT WEAVING	24.3	1.5	3400	4.5	23.0	5.0	7.5	35	40	5.0	1.0	19.2	3.9
4	NE 26/1 COMBED COMPACT WEAVING	26.3	1.5	3300	4.5	23.0	5.0	7.5	40	45	5.0	1.0	20.0	3.9
5	NE 30/1 COMBED COMPACT WEAVING	30.3	1.5	3300	4.5	23.0	5.0	8.0	45	45	4.0	1.0	21.5	3.9
6	NE 32/1 COMBED COMPACT WEAVING	32.3	1.5	3250	4.5	22.0	5.0	8.0	45	45	4.0	1.0	22.2	3.9
7	NE 34/1 COMBED COMPACT WEAVING	34.3	1.5	3250	4.5	22.0	4.5	8.5	50	45	4.0	1.0	22.8	3.9
8	NE 36/1 COMBED COMPACT WEAVING	36.3	1.5	3250	4.5	22.0	4.5	8.5	55	45	4.0	1.2	23.5	3.9
9	NE 40/1 COMBED COMPACT WEAVING	40.3	1.5	3200	4.5	22.0	4.5	9.0	60	50	4.0	1.0	24.8	3.9
10	NE 50/1 COMBED COMPACT WEAVING	50.3	1.5	3200	4.5	22.0	4.2	9.2	80	80	4.0	0.7	27.7	3.9
11	NE 60/1 COMBED COMPACT WEAVING	60.3	1.5	3200	4.5	22.0	4.0	9.5	110	110	3.3	0.6	30.3	3.9
12	NE 80/1 COMBED COMPACT WEAVING	80.3	1.5	3200	4.8	22.0	4.0	10.0	200	180	3.0	0.5	34.9	3.9
13	NE 100/1 COMBED COMPACT WEAVING	100.3	2.0	3200	5.5	22.0	4.0	10.5	300	400	2.8	0.5	39.1	3.9
14	NE 120/1 COMBED COMPACT WEAVING	120.3	2.0	3200	5.5	22.0	4.0	11.0	400	550	2.8	0.5	42.8	3.9