



Amar International

COTTON OPEN END YARNS

OPEN END YARNS FOR WEAVING

Sr. No.	Count of Yarn	CSP	Actual Count	Count CV%	Strength CV%	RKM gm/ Tex UTR	Elongation%	U%	Total Imperfection/km	Hairiness	sh	T.P.I.	T.M.
1	6/1 OPEN END	1600+	6	2.0	5.5	10.3	4.5	9.5	20	0.0	0.0	12.98	5.3
		1700+	6	2.0	5.5	10.9	4.5	9.0	15	0.0	0.0	12.98	5.3
		1800+	6	2.0	5.0	11.5	4.5	9.0	10	0.0	0.0	12.98	5.3
		1900+	6	2.0	5.0	12.2	4.5	8.5	8	0.0	0.0	12.98	5.3
2	7/1 OPEN END	1600+	7	2.0	5.5	10.3	4.5	9.5	20	0.0	0.0	14.02	5.3
		1700+	7	2.0	5.5	10.9	4.5	9.0	15	0.0	0.0	14.02	5.3
		1800+	7	2.0	5.0	11.5	4.5	9.0	10	0.0	0.0	14.02	5.3
		1900+	7	2.0	5.0	12.2	4.5	8.5	8	0.0	0.0	14.02	5.3
3	8/1 OPEN END	1600+	8	2.0	6.0	10.3	4.5	10.0	20	0.0	0.0	14.99	5.3
		1700+	8	2.0	6.0	10.9	4.5	10.0	15	0.0	0.0	14.99	5.3
		1800+	8	2.0	5.5	11.5	4.5	9.5	10	0.0	0.0	14.99	5.3
		1900+	8	2.0	5.5	12.2	4.5	9.0	8	0.0	0.0	14.99	5.3
4	10/1 OPEN END	1600+	10	2.0	6.0	10.3	4.6	10.5	20	0.0	0.0	16.76	5.3
		1700+	10	2.0	6.0	10.9	4.6	10.0	15	0.0	0.0	16.76	5.3
		1800+	10	2.0	5.5	11.5	4.6	9.5	10	0.0	0.0	16.76	5.3
		1900+	10	2.0	5.5	12.2	4.6	9.5	7	0.0	0.0	16.76	5.3
5	12/1 OPEN END	1600+	12	2.0	6.0	10.3	4.6	10.5	20	0.0	0.0	18.36	5.3
		1700+	12	2.0	6.0	10.9	4.6	10.0	15	0.0	0.0	18.36	5.3
		1800+	12	2.0	5.5	11.5	4.6	0.0	0	0.0	0.0	18.36	5.3
		1900+	12	2.0	5.5	12.2	4.6	10.0	10	0.0	0.0	18.36	5.3
6	14/1 OPEN END	1600+	14	2.0	6.0	10.3	4.6	10.5	80	2.0	1.0	19.83	5.3
		1700+	14	2.0	6.0	10.9	4.6	10.0	60	2.0	1.0	19.83	5.3
		1800+	14	2.0	5.5	11.5	4.6	10.0	50	2.0	1.0	19.83	5.3
		1900+	14	2.0	5.5	12.2	4.6	10.0	40	2.0	1.0	19.83	5.3
7	16/1 OPEN END	1600+	16	2.0	6.0	10.3	4.6	10.5	90	3.0	1.0	21.20	5.3
		1700+	16	2.0	6.0	10.9	4.6	10.0	70	3.0	1.0	21.20	5.3
		1800+	16	2.0	5.5	11.5	4.6	10.0	50	3.0	1.0	21.20	5.3
		1900+	16	2.0	5.5	12.2	4.6	10.0	40	3.0	1.4	21.20	5.3
8	20/1 OPEN END	1600+	20	2.0	6.0	10.3	4.6	11.0	90	4.0	1.2	23.70	5.3
		1700+	20	2.0	6.0	10.9	4.6	11.0	70	4.0	1.2	23.70	5.3
		1800+	20	2.0	5.5	11.5	4.6	10.5	60	4.0	1.2	23.70	5.3
		1900+	20	2.0	5.5	12.2	4.6	10.0	50	4.0	1.2	23.70	5.3
9	21/1 OPEN END	1600+	21	2.0	6.0	10.3	4.7	11.0	90	4.0	1.2	24.29	5.3
		1700+	21	2.0	6.0	10.9	4.7	11.0	80	4.0	1.2	24.29	5.3
		1800+	21	2.0	5.5	11.5	4.7	10.5	70	3.8	1.2	24.29	5.3
		1900+	21	2.0	5.5	12.2	4.7	10.0	55	3.8	1.2	24.29	5.3
10	24/1 OPEN END	1600+	24	2.0	6.0	10.3	4.7	11.5	100	4.0	1.2	25.96	5.3
		1700+	24	2.0	6.0	10.9	4.7	11.0	80	4.0	1.2	25.96	5.3
		1800+	24	2.0	5.5	11.5	4.7	11.0	70	3.8	1.2	25.96	5.3
		1900+	24	2.0	5.5	12.2	4.7	11.0	60	3.8	1.2	25.96	5.3
11	30/1 OPEN END	1600+	30	2.0	6.0	10.3	4.7	12.5	285	4.0	1.2	29.03	5.3
		1700+	30	2.0	6.0	10.9	4.7	12.5	250	4.0	1.2	29.03	5.3
		1800+	30	2.0	5.5	11.5	4.7	12.0	230	3.8	1.2	29.03	5.3
		1900+	30	2.0	5.5	12.2	4.7	12.0	200	3.8	1.2	29.03	5.3
12	32/1 OPEN END	1600+	32	2.0	6.0	10.3	4.7	12.5	320	4.0	1.2	29.98	5.3
		1700+	32	2.0	6.0	10.9	4.7	12.5	300	4.0	1.2	29.98	5.3
		1800+	32	2.0	5.5	11.5	4.7	12.0	280	3.8	1.2	29.98	5.3
		1900+	32	2.0	5.5	12.2	4.7	12.0	250	3.8	1.2	29.98	5.3